



ZINCAL COMPACT

6 x K 26 Seale Warrington

*Torons compactés
Compacted strands
Cordones compactados*



Diam. (mm)	AME TEXTILE - FIBER CORE – ALMA EN FIBRA			AME ACIER – STEEL CORE – ALMA METALICA		
	Kg/m	Charge de rupture minimum Min. Breaking load Carga de rotura mínima		Kg/m	Charge de rupture minimum Min. Breaking load Carga de rotura mínima	
		(kN)	(Kg)		(kN)	(Kg)
18	1,23	183	18.600	1,39	196	20.000
19	1,42	210	21.500	1,60	225	22.900
20	1,52	225	23.000	1,72	243	24.700
21	1,71	254	25.900	1,91	270	27.500
22	1,85	274	27.900	2,07	292	29.700
24	2,19	325	33.700	2,47	347	35.400
26	2,65	393	41.400	3,00	431	44.000
28	3,23	479	51.000	3,55	522	53.200
30	3,64	540	57.400	4,03	585	59.700
32	4,13	614	65.400	4,60	667	68.000